



QUALITY REQUIREMENTS FOR TECHNOLOGICAL CHIPS

No	Indicator name	Norm
1.	Bark content, %	no more than 15
2.	Rotting content, %	no more than 5
3.	Mineral impurities content, %	no more than 1
4.	Fractional composition, %	
4.1.	- large	no more than 10
4.2.	- medium	at least 79
4.3.	- small	no more than 10
4.4.	- on a pallet	no more than 1
5.	Charred particles and impurities, %	not allowed
6.	Chip length, mm	10-35
7.	Chip thickness, mm	no more than 5

Remarks:

- Fractional composition is determined in accordance with LST EN 15149-2: 2011.
- Chip length and thickness is adjusted by mutual agreement.
- Technological chips transfer coefficient – 0.42, upon delivery to Grigeo Baltwood UAB, Grigiškės, Vilniaus g. 10.