



QUALITY REQUIREMENTS FOR WASTE PAPER

Waste paper type according to EN 643:2014 (E)	Parameters (%)		
	Humidity	Non-paper components, %	Total undesirable substances, %
Simple types			
<i>1.02 various kinds of paper and cardboard mixtures containing no more than 40% of newspapers and magazines</i>	max 10	max 1.5	max 2.5
<i>1.05 used corrugated cardboard boxes and sheets</i>	max 10	max 1.5	max 2.5
Kraft types			
<i>4.01 unused corrugated cardboard scrap</i>	max 10	max 0.25	max 0.5

Waste paper must not contain:

- non-paper admixtures according to EN 643:2014: metal, plastic, glass, textiles, wood, sand, mortar and synthetic materials, synthetic paper;
- paper and cardboard not suitable for processing: paper and cardboard covered with foil, varnish, textile, foil, paraffin, asphalt, rubber;
- contaminated with chemicals or hazardous substances;
- greasy, metallic, sandpaper, paper and cardboard bags for food, construction and chemicals, cardboard covers all books, back parts of books impregnated with adhesives, labels, cardboard nozzles;
- rotten, moldy, burnt paper;
- intensely dyed paper (black, blue, red, etc., other than white);
- paper egg trays.